

IN THE CLAIMS

Please amend the claims as follows:

Claim 1 (Original): Moulding composition, comprising

a) from 50 to 99.9% by weight of a matrix composed of a thermoplastic polymer  
and

b) from 0.1 to 50% by weight of a matting agent in the form of a (meth)acrylate  
copolymer dispersed in the matrix,

characterized in that

the matting agent is a (meth)acrylate copolymer which has been prepared from the  
following monomers,

b1) from 50 to 95% by weight of methyl methacrylate

b2) from 5 to 50% by weight of C<sub>1</sub>-C<sub>6</sub>-alkyl acrylates

b3) from 0.01 to less than 0.5% by weight of a crosslinking monomer and/or graft-  
linking agent having two or more ethylenically unsaturated radicals capable of  
free-radical polymerization,

b4) from 0 to 20% by weight of one or more other, non-crosslinking ethylenically  
unsaturated monomers capable of free-radical polymerization,

where the entirety of the constituents b1) and b2) and, where appropriate, b3) and/or  
b4) gives 100% by weight, and the glass transition temperature  $T_{mg}$  of the matting agent is at  
least 20°C.

Claim 2 Currently Amended: Moulding comprises ~~composition~~ according to Claim 1,  
characterized in that the matrix a) is composed of a polymethyl methacrylate, of an impact-  
modified polymethyl methacrylate, of a polycarbonate, of a polystyrene, of an acrylate-  
styrene-acrylonitrile graft copolymer (ASA), of a styrene-acrylonitrile (SAN), of a polyester,

of a polyethylene terephthalate (PET), of a glycol-modified polyethylene terephthalate (PETG), of a polybutylene terephthalate plastic (PBT), of a polyvinyl chloride plastic (PVC), of a polyolefin plastic, of a cycloolefin copolymer (COC), of an acrylonitrile-butadiene-styrene (ABS) or of a mixture (blend) of various thermoplastics.

Claim 3 (Currently Amended): Moulding composition according to Claim 1 [[or 2]], characterized in that the matrix a) is an impact-modified polymethyl methacrylate which comprises an impact modifier whose structure has two or three layers.

Claim 4 (Currently Amended): Moulding composition according to ~~one or more of Claims 1 to 3~~ Claim 1, characterized in that the matrix a) is an impact-modified polymer, comprised ~~composed~~ of:

- a1) from 10 to 95% by weight of a coherent hard phase whose glass transition temperature  $T_{mg}$  is above 70°C, composed of
  - a11) from 80 to 100% by weight (based on a1) of methyl methacrylate and
  - a12) from 0 to 20% by weight of one or more other ethylenically unsaturated monomers capable of free-radical polymerization, and
- a2) from 90 to 5% by weight of a tough phase dispersed within the hard phase and having a glass transition temperature  $T_{mg}$  below -10°C, comprised ~~composed~~ of
  - a21) from 50 to 99.5% by weight of a C<sub>1</sub>-C<sub>10</sub>-alkyl acrylate (based on a2)

a22) from 0.5 to 5% by weight of a crosslinking monomer having two or more ethylenically unsaturated radicals capable of free-radical polymerization, and

a23) where appropriate, other ethylenically unsaturated monomers capable of free-radical polymerization,

where at least 15% by weight of the hard phase a1) has covalent linking to the tough phase a2).

Claim 5 (Currently Amended): Moulding composition according to ~~one or more of Claims 1 to 4~~ Claim 1, characterized in that the matting agent b) is a copolymer comprised ~~composed of~~

from 50 to 90% by weight of methyl methacrylate

from 10 to 50% by weight of ethyl acrylate and/or butyl acrylate

from 0.01 to 5% by weight of a crosslinking monomer and/or graft-linking agent having two or more ethylenically unsaturated radicals capable of free-radical polymerization.

Claim 6 (Currently Amended): Moulding composition according to ~~one or more of Claims 1 to 4~~ Claim 4, characterized in that ethylene glycol dimethacrylate is used as crosslinking monomer.

Claim 7 (Currently Amended): Moulding composition according to ~~one or more of Claims 1 to 6~~ Claim 1, characterized in that the matting agent b) has been prepared via emulsion polymerization, and, prior to incorporation into the matrix, has a median particle radius in the range from 100 nm to 10  $\mu$ m.

Claim 8 (Currently Amended): Moulding composition according to ~~one or more of Claims 1 to 7~~ Claim 1, characterized in that a test specimen produced therefrom has roughness variables to DIN 4768 in the range  $R_a$  = from 0.1 to 0.5  $\mu\text{m}$ ,  $R_z$  = from 0.5 to 5.0  $\mu\text{m}$  and  $R_{\text{max}}$  = from 0.5 to 5.0  $\mu\text{m}$ .

Claim 9 (Currently Amended): Process for preparing a moulding composition as claimed in ~~one or more of Claims 1 to 8~~ Claim 1 ~~by in a manner known per se~~ via mixing of the matrix and of the matting agent in the molten state in an extruder, discharging and cooling of the extrudate and then pelletizing of the material.

Claim 10 (Currently Amended): A Moulding composition ~~by which can be produced in a manner known per se by means of~~ extrusion or injection moulding from a moulding composition according to ~~one or more of Claims 1 to 8~~ Claim 1.

Claim 11 (Currently Amended): A Moulding according to Claim 10, characterized in that it is a film, a flat sheet, a corrugated sheet, a multiple-web sandwich panel, a pipe, a rod or an injection-moulded part ~~of any desired shape~~.

Claim 12 (Currently Amended): ~~[[Use of]]~~ The method of using a film produced from the moulding composition according to ~~one or more of Claims 1 to 8~~ Claim 1 for co-lamination to another, optionally printed film material, for back-moulding with a plastics material, for back-foaming with a plastics foam, for extrusion lamination or for the lamination of ~~any desired~~ substrates.